


# Surfaces and bacteria PUFFIN workshop Innovation Center Iceland May 9, 2008

Guðmundur Gunnarsson Innovation Center Iceland



#### What influences bacterial adhesion




- Roughness
- The material
  - Hydrophilic
  - Hydrophobic
- Properties of the bacteria



#### Adhesion of materials to surfaces

Adhesion of oil in air and under water



$$\Delta G = \gamma_{os} - \gamma_{o} - \gamma_{s} = - W_{a}$$
 adhesion if 
$$\gamma_{os} < \gamma_{o} + \gamma_{s}$$

$$\Delta G = \gamma_{os} - \gamma_{ow} - \gamma_{sw} = -W_{a}$$
 adhesion if 
$$\gamma_{os} < \gamma_{ow} + \gamma_{sw}$$

#### Theory of surface tension

• Surface tension between air and material

• 
$$\gamma = \gamma^p + \gamma^d$$

- γ<sup>p</sup> polar componet of surface tension
- γ<sup>d</sup> dispersive component of surface tension

#### Surface tension of some liquids

Substance	γ (m <b>N</b> /m)	γ <sup>ρ</sup> (m <b>N</b> /m)	γ <sup>d</sup> (mN/m)
Water	72.8	51.0	21.8
Glycerol	64	30	34
Ethylene glycol	48	19	29
Dimethyl sulfoxide	44	8	36
Benzyl alcohol	39	11.4	28.6
Toluene	28.4	2.3	26.10
Hexane	18.4	- <	18.4
Acetone	23.7	-	23.7
Chloroform	27.15	\	27.15
Diiodomethane	50.8	_	50.8



# Surface tension between two phases

Interfacial tension between two phases (a and b) can be expressed in terms of the two components for each phase

$$\begin{aligned} \gamma_{ab} &= \gamma_a + \gamma_b - 2\sqrt{(\gamma_a^p \gamma_b^p)} - 2\sqrt{(\gamma_a^p \gamma_b^q)} \\ 2\sqrt{(\gamma_a^d \gamma_b^d)} \end{aligned}$$

#### Adhesion of oil to surfaces

- Possible to calculate work of adhesion of oil to surfaces
  - Surface in air
  - Surface under water



### Work of adhesion of a mineral oil to various solid surfaces in air and in water

	$W_{\rm oas}/{ m mJ}{ m m}^{-2}$	$W_{ m ows}/{ m mJm}^{-2}$	_
Quartz	72	9	-
Crown glass	65	20	
Nylon 6,6	57	51	
Polyester	53	54	For mineral oil
PEŤ	55	67	$\gamma_0^d = 25 \text{ mJ m}^{-2} \text{ and } \gamma_0^p = 0$
PVC	57	73	1 <sub>0</sub> = 3 3 1 <sub>0</sub> 3
Skin - forehead (a)	64	64	
Skin – forearm (a)	62	89	
Tooth enamel (b)	63	84	
Polyethylene	55	86	
Polypropylene	52	99	$W_{oas}$ = work of adhesion
Human hair (c)	49	74	in air
Silicone DC200 film on glass	47	80	$W_{\text{ows}}$ = work of adhesion
C18 amine monolayer on	47	102	—in water
glass			
PTFE	42	91	
FC721 (3M coating) on	34	95	
glass			Clint and Wicks 2001




- Oil adheres well to hydrophilic material in air
- Oil adheres badly to hydrophilic materials in water

Order in water reverse to that in air



#### Water drop on a surface




- § Drop spreads
  - § hydrophilic, low contact angle
  - § High surface energy

- § Drop does not spread
  - § hydrophobic, high contact angle
  - § Low surface energy



#### Contact angle




```
Θ = contact angle
γ = surface
tension or
surface energy
(unit: mN/m or
mJ/m²)
```

- Surface energy of a surface can be determined by mesuring contact angle of different liquids with the surface
- Contact angle of water
  - Hydrophobic surface, ⊖ > ca. 70 80 °C
  - Hydrophilic surface, ⊖ < ca. 50 60 °C

#### Roughness and contact angle

 Contact angle of a water drop on a rough hydrophobic surface is higher than on a smooth surface of the same material



$$\cos\theta = f_1 \cos\theta_0 - f_2$$
 Cassies equation

f<sub>1</sub> = proportional surface area of material1)

f<sub>2</sub> = proportional surface area of pores or air


$$\theta_0 = 90^{\circ}$$
,  $f_1 = f_2 = 0.5 \rightarrow \theta = 120^{\circ}$ 

$$\theta_0 = 110^{\circ} , f_1 = 0.2 \rightarrow \theta = 154^{\circ}$$

"SUPERHYDROPHOBIC"




#### Superhydrophobic surface



http://www.aip.org/png/2006/247.htm

#### Self cleaning



http://www.nees.uni-bonn.de/lotus/en/lotus\_effect\_html.html






#### Superhydrophilic surface


- A drop of water on a superhydrophlic surface spreads, disapears and form a film
- Dew can not form on a superhydrophilic surface
- Raindrops impinging on a superhydrophilic surface form a film that drains of the surface
- Water can penetrate between dirt and surface contributing to self cleaning effect
- A superhydrophilic surface dries fast



#### Photocatalytic self cleaning surfaces

- Surface is coated wth titania nanoparticles
- Ilumination with UV light results in a superhydrophilic surface
- Free radicals (hydroxyl, oxygen) form and break down organic matter on the surface









## Applications of photocatalytic surfaces

- Self cleaning windows
  - On the market in many countries
- Self cleaning ceramic tiles
  - UV light needed
  - Self clening with indoor light beeing developed
- Sprays with photocatalysts
  - Curtains etc.





#### Superhydrophilic silica based coatings




Water can penetrate between dirt and surface Help in washing away impurities with rain

#### Easy to clean coatings

- Low surface energy coating that give a high water contact angle, 110°
- Low adhesion forces between surface and dirt - dirt can easily by wiped away.
- Previous results have shown that bacteria in water suspensions adhere better to stainless steel with easy to clean coating than to stainless steel itself.

# Modification of surfaces with surface active polymers

 Mirapol Surf-S polymers adsorb on hard surfaces from diluted water-based formulations




Step 1 polymer in solution approaches surface



water sheeting effect

Step 2
polymer adsorbs onto surface

The polymer modifies the surface's energy, making it more hydrophilic



Rhodia.com


Added to cleaning formulation

Polymer not easily washed away

#### Easy to clean

Next cleaning easier

#### Immediate soil removal when rinsed under cold tap water



#### Why measure surface energy?

- Adhesion of bacteria to a surface is influenced by the surface energy of the surface and the surface energy of the bacteria
- Bacteria can be hydrophilic or hydrophobic
- Hydrophobic bacteria adhere better to all surfacs than hydrophilic bacteria
- All bacteria adhere better to hydophobic than hydrophilic surfaces

### Surface energy of bacteria can be measured

Material	Surface energy (mN/m)
Psuedomnas putida*	35.3
Listeria monocytogenes*	49.1
Glycerol	64
Hexane	18.4
Glass	64.4
Stainless steel	45.9
Polyethylene	31
Teflon	17.6
Water	72.8

Hydrophilic materials

high surfaceenergy


Hydrophobic materials

- low surface energy

\*Bacteria isolated from Icelandic fishing Industry



## Free energy of adhesion of bacteria to a surface



 $\gamma_{\rm bw}$  = surface energy between bacteria and water  $\gamma_{\rm sw}$  = surface energy between surface and water  $\gamma_{\rm bs}$  = surface energy between surface and bacteria

# Adhesion can occur if free energy of adhesion negative

	Free energy of adhesion of bacteria to surface (mJ/m²)			
Surface	Pseudomonas putida	Listeria monocytogenes		
Polyethylene	-55	-8		
Stainless steel	-16	24		

- •Pseudomonas has a tendency to adhere to most surfaces
- •Psuedomonas is very common in the fish industry
  - can be explained by above results

